

# 7032

## CAST METAL SEALANT

KATS 7032 is an acrylic water-based sealant that has been formulated to eliminate porosity leaks through the process of polymer impregnation. It is suitable for use on ferrous and non-ferrous castings and carbon fiber products.

KATS 7032 fills and covers small voids that may be inherent in the materials. It will enhance the bonding capability of powder coats, water based paints, and other types of coatings.

Surface must be clean and dry. The surface temperature can be up to 200°F (93.3°C).

The item to be coated can be placed in a vat of product or a generous flow of product can be poured over the surface.

Allow the coating to dry 20-30 minutes at room temperature before handling.

Wet Film Thickness: 0.5 - 1.0 mil (12.7 - 25.4 microns)Dry Film Thickness: 0.1 - 0.2 mil (2.5 - 5.1 microns)

Coverage: 2000 ft<sup>2</sup>/gal - 4000 ft<sup>2</sup> /gal (49.3m<sup>2</sup>/l - 98.5m<sup>2</sup>/l)

#### **BENEFITS:**

- · Solidifies to block differential pressure and leaks
- · Reduces rejected material due to voids
- · Improved machinability of powder metal components
- Contains only 0.1 lb/gal (12 gm/liter) of VOC's
- Fast drying
- Dries clear
- · Non-flammable
- · Environmentally safe

#### **APPLICATIONS:**

Use KATS 7032 to seal porosity on cast metal such as cast iron, aluminum, magnesium and bronze. Also suitable for use on powder metal components.

- Engines
- Manifolds
- Coolant connectors
- Transmission cases
- Pump housings
- Fluid power components

TEST METHOD	DESCRIPTION	TYPICAL CHARACTERISTIC
MKA 02W001	Pressure Test Bubbling of Coated Item at 25 psig	None
ASTM D-3359	Adhesion Test Paint Loss	None
MKA 02W039	Pressure Test Leaks after 60 days at 300°F (149°C)	None
ASTM D-2196 Modified	Brookfield Viscometer Spindle 1 @60 rpm @ 72°F (22°C)	4-10 cps

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

#### **PACKAGING**

260 Gallon	55 Gallon	5 Gallon
Totes	Drums	Pails

### A Division of The Whitmore Manufacturing Company

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108 An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • www.katscoatings.com

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly. Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.